

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claim 1 (currently amended): Polyethylene molding material having a bimodal molecular weight distribution which has an overall density of $> 0.948 \text{ g/cm}^3$ and an $\text{MFI}_{190/5}$ $\text{MFI}_{5/190}$ of $< 0.2 \text{ dg/min}$, characterized in that it comprises an amount of from 35 to 65% by weight of low-molecular-weight ethylene homopolymer A which has a viscosity VN_A in the range from 40 to 90 cm^3/g , a melt flow index $\text{MFI}_{190/2.16 A}$ in the range from 40 to 2000 dg/min and a density d_A of $\geq 0.965 \text{ g/cm}^3$, and an amount of from 35 to 65% by weight of high-molecular-weight ethylene copolymer B which has a viscosity number VN_B in the range from 500 to 2000 cm^3/g , a melt flow index $\text{MFI}_{190/5 B}$ in the range from 0.02 to 0.2 dg/min and a density d_B in the range from 0.922 to 0.944 g/cm^3 , and in that the fraction obtained during a preparative TREF analysis at a temperature of $78^\circ\text{C} \pm 3 \text{ K}$ using p-xylene has an average molecular weight of $\geq 200,000 \text{ g/mol}$.

Claim 2 (original): Pipe produced from a polyethylene molding material according to claim 1, characterized in that it has a stress cracking resistance of $\geq 1500 \text{ h}$ and a fracture toughness FT of $\geq 9 \text{ MJ/mm}^2$.

Claim 3 (original): Pipe according to claim 2, characterized in that it has a flexural creep modulus, measured in accordance with DIN 54852-Z4, of $\geq 1350 \text{ N/mm}^2$.

Claim 4 (previously amended): Pipe according to claim 2, characterized in that has been produced from an ethylene polymer having a bimodal molecular weight distribution which comprises comonomers having from 4 to 10 carbon atoms in an amount of from 2.5 to 4% by weight in the relatively high-molecular-weight fraction B.

Claim 5 (previously amended): Pipe according to claim 3, characterized in that the low-molecular-weight fraction of the ethylene polymer has a melt flow index $MFI_{2.16/190^{\circ}C}$ in the range from 200 to 800 g/10 min.

Claim 6 (previously amended): Pipe according to claim 3, characterized in that the ethylene polymer has a melt flow index $MFI_{2.16/190^{\circ}C}$ of ≤ 0.19 dg/min.

Claim 7 (previously amended): Pipe according to claim 2, characterized in that it has a notched impact strength NIS_{ISO} , measured in accordance with ISO 179 (DIN 53453), of at least 25 mJ/mm² at -20°C and of at least 40 mJ/mm² at +23°C.

Claim 8 (previously amended): Pipe according to claim 2, characterized in that it has a resistance to rapid crack growth, measured in accordance with ISO/DIS 13477 on a pipe in pressure class PN 10 having a diameter of 110 mm (S4 test), of ≥ 20 bar.

X Claim 9 (previously amended): A method of transporting gases through a pipe according to claim 2 including the step of flowing gases through the pipe.

X Claim 10 (previously amended): A method of transporting water through a pipe according to claim 2 including the step of flowing water through the pipe.